

Technical specifications

| Article | Format | Weight/piece | Pieces/m ² (with joint of 12mm) | Average compressive strength | Water absorption | Initial water absorption | Dimensions / Tolerance | Durability – Frost resistance / Active soluble salt content |
|-----------------|--------------------|--------------|--|------------------------------|------------------|------------------------------|------------------------|---|
| Classics | | | | | | | | |
| Alyssum | WF(210 x 100 x 50) | ± 1,81 kg | ± 72 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,18 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Veldbloem | WDF(215x100x65) | ± 2,18 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Barok "83" | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Duinbergen | WDF(215x100x65) | ± 2,18 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Hocht | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Maldon Antique | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Neo Romaans | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Romaans | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Rood | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Welham Antique | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Cie Classic | WDF(215x100x65) | ± 2,27kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |

| Article | Format | Weight/piece | Pieces/m ² (with joint of 12mm) | Average compressive strength | Water absorption | Initial water absorption | Dimensions / Tolerance | Durability – Frost resistance / Active soluble salt content |
|-------------------|--------------------|--------------|--|------------------------------|------------------|------------------------------|------------------------|---|
| Rainbow | | | | | | | | |
| Amarillo | WF(210 x 100 x 50) | ± 1,81 kg | ± 72 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,18 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Atlasgrijs | WF(205 x 100 x 50) | ± 1,96 kg | ± 74 | ≥ 25 N/mm ² | ≤ 10% | ± 1,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(210x100x65) | ± 2,38 kg | ± 59 | ≥ 25 N/mm ² | ≤ 10% | ± 1,5kg/(m ² min) | T1/R1 | F2/S2 |
| Bianco | WF(205 x 100 x 50) | ± 1,96 kg | ± 74 | ≥ 25 N/mm ² | ≤ 10% | ± 1,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(210x100x65) | ± 2,38 kg | ± 59 | ≥ 25 N/mm ² | ≤ 10% | ± 1,5kg/(m ² min) | T1/R1 | F2/S2 |
| Gobi | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Lavagrijs | WF(205 x 100 x 50) | ± 1,96 kg | ± 74 | ≥ 25 N/mm ² | ≤ 10% | ± 1,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(210x100x65) | ± 2,38 kg | ± 59 | ≥ 25 N/mm ² | ≤ 10% | ± 1,5kg/(m ² min) | T1/R1 | F2/S2 |
| Nero Zwart Mangan | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Paepsteen | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Pampas | WF(210 x 100 x 50) | ± 1,88 kg | ± 72 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,27 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Plaza | WF(210 x 100 x 50) | ± 1,81 kg | ± 72 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| | WDF(215x100x65) | ± 2,18 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |

| Heritage | | | | | | | | |
|-----------------|-----------------|-----------|------|------------------------|-------|------------------------------|-------|-------|
| Oud Bokrijk | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Bologne | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Brussel | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Diest | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Kortemark | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Watou | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 17% | ± 2,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oud Wezent | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |
| Oude Paep | WDF(215x100x65) | ± 2,28 kg | ± 58 | ≥ 25 N/mm ² | ≤ 14% | ± 4,5kg/(m ² min) | T1/R1 | F2/S2 |

Disclaimer The brick colours shown in this brochure are only as accurate as the printing process will allow. Customers are advised to obtain samples. Technical data are approximate.